

**AMENDMENTS TO THE CLAIMS**

**This listing of claims will replace all prior versions and listings of claims in the application:**

**LISTING OF CLAIMS:**

1. (previously presented): A process for manufacturing an electret article, comprising passing melt-extruded thermoplastic resin fibers through a mist space substantially formed from droplets of a polar liquid wherein the average diameter of said droplets is less than 20  $\mu\text{m}$ , and then collecting the fibers, wherein said thermoplastic resin fibers contain electrical-chargeability enhancing agents, and wherein the fibers are not wetted upon passing through said mist space and are not subjected to a drying step after passing through said mist space.

2. (canceled).

3. (currently amended): The process according to claim 1, wherein a ~~resin-droplet~~<sup>droplet</sup> to resin percentage of the formula:

$$(W_p/W_f) \times 100$$

wherein  $W_p$  denotes the amount of said droplets forming said mist space and sprayed to a unit volume thereof within a certain period of time, and  $W_f$  denotes the amount of said melt-extruded thermoplastic resin passed through said mist space within a certain period of time,

is 500 or more.

4. (previously presented): The process according to claim 1, wherein a heated gas is blown onto said melt-extruded thermoplastic resin fibers.

5. (previously presented): The process according to claim 1, wherein a volume specific resistivity of said thermoplastic resin is  $10^{14} \Omega \cdot \text{cm}$  or higher.

6. (original): The process according to claim 5, wherein a volume specific resistivity of said thermoplastic resin is  $10^{16} \Omega \cdot \text{cm}$  or higher.

7. (previously presented): The process according to claim 1, wherein said polar liquid is water.

8. (previously presented): The process according to claim 1, wherein said electrical-chargeability enhancing agent is at least one compound selected from a group consisting of a hindered amine compound, a metallic salt of a fatty acid, a metallic oxide, and an unsaturated carboxylic acid-modified high-molecular compound.

9. (previously presented): The process according to claim 1, wherein the average diameter of said droplets is 15  $\mu\text{m}$  or less.

10. (previously presented): An apparatus for manufacturing an electric article, comprising (1) a means for melt-extruding a thermoplastic resin containing electrical-chargeability enhancing agents to form thermoplastic resin fibers; (2) a means for spraying

droplets consisting essentially of a polar liquid to a space downstream of a direction of said thermoplastic resin extruded from said means for melt-extruding a thermoplastic resin, to thereby form a mist space, the average diameter of said droplets being less than 20  $\mu\text{m}$ ; and (3) a means for collecting said thermoplastic resin fibers which have been passed through said mist space without subjecting said fibers to a drying step.